

# Vinyl Chloride Monomer (VCM) 氯乙烯

Standard 执行标准: Q/321283GNH08-2014

| Parameters 指标名称                     | Specifications 指 标   |                    |                    |
|-------------------------------------|----------------------|--------------------|--------------------|
|                                     | Premium Grade<br>优等品 | First Grade<br>一等品 | Qualified<br>合 格 品 |
| VCM 氯乙烯(g/kg) ≥                     | 999.5                | 999.2              | 999.0              |
| Acetylene 乙炔(wppm) ≤                | 2.0                  | 5.0                | 5.0                |
| Ethylene Acetylene<br>乙烯基乙炔(wppm) ≤ | 20.0                 | 20.0               | 20.0               |
| Acetic aldehyde 乙醛(wppm) ≤          | 5.0                  | 5.0                | 5.0                |
| 1, . Butadiene 1,3-丁二烯(wppm) ≤      | 10.0                 | 10.0               | 10.0               |
| Hydrochloric ether 氯代烃(wppm) ≤      | 100.0                | 150.0              | 200.0              |
| 1,1EDC+1,2EDC(wppm) ≤               | 10.0                 | 10.0               | 25.0               |
| Water 水(wppm) ≤                     | 100.0                | 200.0              | 200.0              |
| Iron 铁(wppm) ≤                      | 0.5                  | 0.5                | 1.0                |
| Acidity 酸度(wppm) ≤                  | 1.0                  | 1.0                | 1.0                |
| Solid Residue 固体干渣(wppm) ≤          | 30.0                 | 40.0               | 50.0               |

Available for sale

500,000 ton per annum